

Find the right
product for
your application



FLANGE TYPE

Rigid Machined Flange

LOCTITE® 518™
LOCTITE® 515™
LOCTITE® 510™
LOCTITE® 573™
LOCTITE® 5127™

Stamped Flange

LOCTITE® SI 5699™
LOCTITE® SI 5900™
LOCTITE® SI 587™
LOCTITE® SI 596™



Rigid Machined Flange

GASKETING PRODUCTS



518™
General Purpose

Colour: Red
Viscosity: 4,000,000 cP Thixotropic
Temperature Resistance: Up to 150°C
Cure Method: Anaerobic



515™
General Purpose

Colour: Purple
Viscosity: 1,500,000 cP Thixotropic
Temperature Resistance: Up to 150°C
Cure Method: Anaerobic



510™
High Temperature

Colour: Opaque Pink
Viscosity: 400,000 cP Thixotropic
Temperature Resistance: Up to 204°C
Cure Method: Anaerobic



573™
Slow Curing

Colour: Green
Viscosity: 23,250 cP Thixotropic
Temperature Resistance: Up to 150°C
Cure Method: Anaerobic



5127™
Highly Flexible

Colour: Blue
Viscosity: 120,000 cP Thixotropic
Temperature Resistance: Up to 150°C
Cure Method: Anaerobic

Stamped Flange

GASKETING PRODUCTS



SI 5699™
Chemical Resistant

Colour: Grey
Viscosity: Paste
Temperature Resistance: 204°C
Cure Method: Moisture



SI 5900™
Instant Seal

Colour: Black
Viscosity: Paste
Temperature Resistance: 232°C
Cure Method: Moisture



SI 587™
High Adhesion

Colour: Blue
Viscosity: Paste
Temperature Resistance: 260°C
Cure Method: Moisture



SI 596™
High Temperature

Colour: Red
Viscosity: Paste
Temperature Resistance: 316°C
Cure Method: Moisture